

# D3O<sup>®</sup> BIO



## D3O<sup>®</sup> Bio is the world's leading clear plant-based impact protection material.

Providing the same protection D3O is renowned for, D3O<sup>®</sup> Bio saves on fossil-based resources and can be used in both crystal-clear and colour products.

D3O<sup>®</sup> Bio helps reduce water consumption and allows for sustainable waste management, offering the ability to recycle material waste from the production process directly back into it, avoiding post-industrial waste.

Compatible with injection moulding or similar processes and currently used for the protection of consumer electronics, D3O<sup>®</sup> Bio is the solution to protect devices, people and planet.

### Typical Properties

|                                       | Method reference*      | Test Condition | D3O <sup>®</sup> Bio |
|---------------------------------------|------------------------|----------------|----------------------|
| Density (kg/m <sup>3</sup> )          | ISO 845:2009           | -              | 1160.0               |
| MFR (g/10 min)                        | ISO 1133               | 200°C, 2.16 kg | 9.9                  |
| Hardness (Shore A)                    | ASTM D2240 - 05 (2010) | 3s             | 93.3                 |
| Tensile Strength at Break (MPa)       | ISO 37:2017 Type 1     | 500mm/min      | 20.7**               |
| Tensile Elongation at Break (%)       | ISO 37:2017 Type 1     | 500mm/min      | 499.3**              |
| Tear Strength (N/mm)                  | ASTM D624 Type T       | 50mm/min       | 8.4**                |
| Flexural Modulus (kPa)                | DTS052                 | -              | -                    |
| Shrinkage (at 150°C)                  | -                      | -              | 0.8%                 |
| Abrasion Resistance (mg/100 cycles)   | ISO 5470-1             | H18, 9.8N      | 4.5**                |
| Transparency (%)                      | DTS086                 | -              | 81.0                 |
| Plant-based content (%)               | -                      | -              | 45.0                 |
| Suitable for opaque coloured products | -                      | -              | ✓                    |
| Suitable for translucent products     | -                      | -              | ✓                    |
| Suitable for clear products           | -                      | -              | ✓                    |

#### Notes:

- Water cooling recommended on bottom of the hopper
- Cycle times dependant on section thickness and temperature
- Parts must be sufficiently cooled (20-40s) before demoulding to prevent distortion
- Part must be removed carefully to prevent deformation
- The shelf life of the TPE granules is 12 months from delivery if storage instructions are observed and the product is stored in the unopened original D3O TPE packaging. Store in dry conditions at room temperature (15–30 °C) away from heat sources and direct sunlight.
- This material is plant based, which may cause visual irregularities in the products

### Material Features:

- Same trusted D3O<sup>®</sup> Protection
- Suitable for clear and colour products
- Leading plant-based content
- Made from renewable resources
- Optimal and consistent melt flow TPE grade for trouble-free, high-quality moulding

### Injection Moulding Conditions

|                     |                    |                                   |
|---------------------|--------------------|-----------------------------------|
| Drying Conditions   | Temperature (°C)   | 70                                |
|                     | Time (h)           | 4                                 |
|                     | Equipment          | Dehumidified drying oven (vacuum) |
| Moulding Conditions | Screw Speed        | Medium                            |
|                     | Injection Speed    | Medium - Low                      |
|                     | Injection Pressure | Medium - Low                      |
|                     | Holding Pressure   | High                              |
|                     | Back Pressure      | Medium - Low                      |
|                     | Feeder (°C)        | 190 - 230                         |
|                     | Zone 1 (°C)        | 180 - 220                         |
|                     | Zone 2 (°C)        | 180 - 215                         |
|                     | Nozzle (°C)        | 170 - 180                         |
| Mould (°C)          | 50                 |                                   |

©2023 Design Blue Limited. All rights reserved.

For full details including material properties and product tolerances, please request SOQ document from a D3O representative. The information provided is not intended to and does not create any warranties, expressed or implied, including any warranty of merchantability of fitness for a particular purpose. This data sheet shall not be reproduced or amended without the written consent of Design Blue Limited.

\*Values shown represent typical product characteristics

\*\*Estimated

For commercial queries please visit <https://www.d3o.com/contact-us>